

SPECIFICATION AMENDMENTS

Please replace Table 1 on page 53 with Table 1 as shown below. Also shown below is a clean copy of Table 1 for purposes of scanning.

Table 1

Substrate No.	Surface configuration parameters of substrate					Remarks
	Ra (μm)	Mr2 (%)	100-Mr2 (%)	Rvk (μm)	A2	
1	0.55	88.8	11.2	0.98	5.49	Invention
2	0.48	88.6	11.4	0.77	4.39	Invention
3	0.42	89.3	10.7	0.66	3.53	Invention
4	0.63	88.3	11.7	1.35	7.90	Invention
5	0.81	86.9	13.1	1.74	11.40	Invention <u>Comparative</u>
6	0.66	78.8	21.2	1.56	16.54	Comparative

Table 1

Substrate No.	Surface configuration parameters of substrate					Remarks
	Ra (μm)	Mr2 (%)	100-Mr2 (%)	Rvk (μm)	A2	
1	0.55	88.8	11.2	0.98	5.49	Invention
2	0.48	88.6	11.4	0.77	4.39	Invention
3	0.42	89.3	10.7	0.66	3.53	Invention
4	0.63	88.3	11.7	1.35	7.90	Invention
5	0.81	86.9	13.1	1.74	11.40	Comparative
6	0.66	78.8	21.2	1.56	16.54	Comparative